



RESTRICTED

PRETORIA METAL PRESSINGS
a division of Denel (Pty) Ltd

SPECIFICATION FOR BAR STEEL BRIGHT Ø 21,0mm BASED ON SAE 1017

Should a Tenderer/Vendor not be able to meet the requirements of this document, it must declared in writing to the Buying Manager at the time of tendering/receipt of an order.

DOCUMENT No.: **750 2543** ISSUE 2

DBS: **B11**
CODE No.: **07750254307**

TENDER

DATE 2023-09-11
COPY NO: 32
ISSUED BY: IP

(1483.doc)

RESTRICTED

DOC SERVER

RESTRICTED



PRETORIA METAL PRESSINGS a division of DENEL (Pty.) Ltd.

APPROVAL PAGE

COMPILED BY

I. P. PRETORIUS
Configuration Control name

[Signature]
Signature

2008-09-02
Date

APPROVED BY

H. S. STORM
Production User name

[Signature]
Signature

2008-09-15
Date

HD Vermaak
Production Manager name

[Signature]
Signature

2008/09/18.
Date

Ced ulene
Acceptance Authority name

[Signature]
Signature

2008/10/03
Date

ORIGINAL COPY SIGNED

AMENDMENT HISTORY SHEET

ISSUE	DETAILS	ECP NO	DONE BY	DATE
2	Change copper content specification.	E2/089/08MC	I.P. <u>[Signature]</u>	19/08/2008

Should a Tenderer/Vendor not be able to meet the requirements of this document, it must be declared in writing to the Buying Manager at the time of tendering/receipt of an order.

TENDER

DATE: 2023-09-11
COPY NO: 32
ISSUED BY: IP

**TABLE OF CONTENTS**

PARA	SUBJECT	PAGE NO
1.	SCOPE	4
2.	APPLICABLE DOCUMENTS	4
3.	REQUIREMENTS	4
3.1	General material requirements	4
3.1.1	Product characteristics	4
3.1.2	Chemical, mechanical and metallurgical properties	4
3.1.2.1	Chemical composition	4
3.1.2.2	Mechanical properties	5
3.1.2.3	Metallurgical properties	5
3.1.3	Workmanship	5
4.	QUALITY ASSURANCE PROVISIONS	5
4.1	Responsibility for inspection	5
4.2	Special tests and examinations	5
4.3	Quality conformance inspection	6
4.3.1	Lot information	6
4.4	Test methods	6
5.	PREPARATION FOR DELIVERY	6
5.1	Packing	6
5.2	Package marking	6
5.3	Documentation for delivery	7
6.	NOTES	7

Should a Tenderer/Vendor not be able to meet the requirements of this document, it must be declared in writing to the Buying Manager at the time of tendering/accept of an order.

TENDER

DATE 2023-09-11

COPY NO: 32

ISSUED BY: IP

1. SCOPE

- 1.1 This specification covers aluminium killed bar steel based on SAE 1017 that conforms to this specification.

2. APPLICABLE DOCUMENTS

ASTM E92
DIN 50602
ASTM E112

Should a Tenderer/Vendor not be able to meet the requirements of this document, It must declared in writing to the Buying Manager at the time of tendering/receipt of an order.

3. REQUIREMENTS3.1 General material requirements

The material shall be supplied as bright bar in the as hot rolled and peeled condition.

3.2 Product characteristics

- 3.2.1 The material shall be supplied as bright bar in lengths of 3-6m. The maximum variation in length in a batch shall not exceed 50cm.

+0,00mm

- 3.2.2 The diameter shall be 21,0mm -0,13mm

- 3.2.3 Straightness deviation shall not exceed 1,5mm/meter.

3.3 Chemical, mechanical and metallurgical properties3.3.1 Chemical composition (Cast analysis)

ELEMENT	SPECIFICATION (%)	AIM
Carbon (C)	0,16 – 0,21	0,18 – 0,2
Silicon (Si)	0,15 maximum	0,1 maximum
Manganese (Mn)	0,4 – 0,6	-
Sulphur (S)	0,015 maximum	0,01 maximum
Phosphorus (P)	0,02 maximum	-
Chromium (Cr)	0,1 maximum	-
Nickle (Ni)	0,1 maximum	-
Aluminium (Al)	0,02 – 0,06	0,02 – 0,04
Molybdenum (Mo)	0,05 maximum	-
Copper (Cu)	0,11 maximum	0,08 maximum
Nitrogen (N)	0,008 maximum	-
Sum of Carbon and Manganese	0,6 – 0,75	-

TENDER

DATE 2023-09-11
COPY NO: 32
ISSUED BY: IP



3.3.2 Mechanical properties

Internal Hardness (HV 10): 150 Vickers maximum

3.3.3 Metallurgical properties

Inclusion count: The inclusion count shall be done according to DIN 50602, method M. Inclusion ratings per sample must not exceed the following indices:
0.5; 1.5; 2.5; 3.5; 4.5; 5.3; 6.3; 7.3; 8.3; 9.3

Ferrite grain size: 6 – 8 (ASTM E112)

3.4 Workmanship

3.4.1 The material must be free from piping, cracks, laps, porosity and macroscopic inclusions, for example slag inclusions.

3.4.2 The material must be free from surface defects.

3.4.3 The structure shall be homogeneous, consisting of ferrite and pearlite.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection

4.1.1 Unless otherwise specified in the contract or order, the supplier is responsible for the performance of all inspection requirements as specified herein.

4.1.2 Except as otherwise specified, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements.

4.1.3 The purchaser or his representative reserves the right of inspection of Laboratory Certificates of raw materials and components used for the manufacture of the material.

4.1.4 The supplier shall be responsible for making available to the purchaser all facilities necessary if required, for inspection of the material.

4.1.5 The supplier will be responsible for the implementation of an applicable quality management system to assure the appropriate quality of the product. The purchaser reserves the right to audit the supplier's production facilities at all times to ascertain whether quality requirements are being met.

Should a Tenderer/vendor not be able to meet the requirements of this document, it must be declared in writing to the Buying Manager at the time of tendering/receipt of an order.

TENDER

DATE 2023-09-11

COPY NO: 32

ISSUED BY: IP



4.2 Special tests and examinations

- 4.2.1 Special test methods such as ultrasonic testing, magnaflux, sulphur prints etc., must be used to assure that the material is free from harmful defects, ie., piping, macroscopic inclusions, cracks, porosities, etc.
- 4.2.2 Prior to final rolling or dispatch of the material, at least 12 samples, randomly taken from appropriate billets must be forged to 30 – 50 mm diameter or square and submitted for evaluation by the purchaser. Only if the abovementioned samples conforms to the specification with respect to chemical analysis and inclusion counts, may the material be rolled or dispatched, however, notwithstanding the above, the final acceptance of the finished product will take place at the premises of the purchaser.

4.3 Quality conformance inspection

4.3.1 Lot information

A lot shall consist of one or more batches of material produced by one manufacturer in accordance with the same specifications under one continuous set of operating conditions. All material must be of the same cast or heat.

If the quantity is such that more than one cast is required, material of the same cast shall be grouped together. Each case or bundle shall be clearly identifiable as to the relevant cast number.

The supplier shall ensure that all deliveries to the end user are fully traceable by lot number and that identification records be supplied to the end user to match lot numbers with inspection records.

4.4 Test methods

Hardness test: In accordance with ASTM E92

Inclusion count: In accordance with DIN 50602

Grain size: In accordance with ASTM E112

Should a Tenderer/Vendor not be able to meet the requirements of this document, it must be declared in writing to the Buying Manager at the time of tendering/receipt of an order.

TENDER

DATE 2023-09-11

COPY NO: 32

ISSUED BY: IP



5. PREPARATION FOR DELIVERY

5.1 Packing

5.1.1 To be strapped in bundles suitable for forklift handling using 4 evenly spaced steel straps. The maximum mass shall not exceed 2 500 kg unless otherwise agreed between the supplier and purchaser.

5.1.2 In the case of an overseas supplier the bundles shall be packed in a seaworthy condition using suitable wooden boxes secured by steel straps. The gross mass of the strapped boxes may not exceed 2 600 kg.

5.1.3 If containers are used for transportation of the material, open top containers must be used. The wooden boxes must be properly stacked in the container with spaces of ± 150 mm between them.

5.2 Package marking

All bundles, boxes and/or containers to be legibly and durably marked with the following details on suitable labels:

5.2.1 Document and order number.

5.2.2 Name of supplier.

5.3 Documentation for delivery

Should a Tenderer/Vendor not be able to meet the requirements of this document, it must be declared in writing to the Buying Manager at the time of tendering/receipt of an order.

The following documents must be forwarded with each consignment of material:

5.3.1 The original specification, which accompanied the order in the case of a single consignment or the final consignment of, staggered deliveries.

5.3.2 A certificate of conformance/analysis stating all the results of the tests conducted by the supplier during manufacture and final acceptance.

5.3.3 Certificate of acceptance issued by the end user or his duly representative or a letter from the end user for the release of the consignment for shipment in the case of an overseas supplier.

5.3.4 The supplier's delivery note shall clearly state the relevant order and document number.

6. NOTES

If the supplier of the material is not the original manufacturer, the full name and address of the manufacturer must be supplied in writing during tender.

TENDER

DATE 2023-09-11

COPY NO: 32

ISSUED BY: IP