

Specifications - K - Wall Covering	
Key Value	Keynote Text
K1: Smooth plaster	(A) Interior plaster: Plaster shall be not less than 12mm or more than 20mm thick 1x coat of sand/cement (4:1) smooth plaster finished with a steel float or wooden float if tiled. (B) Exterior plaster: Plaster shall be not less than 9mm or more than 16mm thick coat (5:1) of sand/cement smooth plaster finished with a wood float. All plaster splashes, loose material and surface contamination to be removed by brushing or scraping. Using approved filler, all defects to be made good. Remove powdery residues once dry before painting.
K2: Textured plaster	Plaster shall be not less than 9mm or more than 16mm thick coat (5:1) of sand/cement mix with small stone aggregate mixed in. Surface to be raked from multiple directions with an even and straight wooden plank or straight edge to achieve the required texture. Finished surface to be even and plumb with varying holes and indentations. All plaster splashes, loose material and surface contamination to be removed by brushing or scraping. Using approved filler, all defects to be made good. Remove powdery residues once dry before painting. Provide a sample of texture plaster for approval before applying technique to entire building.
K11-a: Plastered window sill	Window reveals, returns, sills not exceeding 150mm wide to be plastered and painted as per wall finishes. For exterior sills - to be sloped away from building at an angle of 3 degrees. For interior sills - no slope required. All corners to be rounded smooth and even.

DRAWING TITLE SPECIFICATIONS - WALL COVERINGS	CLIENT NAME CITY OF MBOMBELA		
	Sheet Issue Date	Drawn by	Current Rev. Date
PROJECT TITLE THEKWANE SPORT FIELD - GATE HOUSE	2023/09/15	FB   DDK	2023/09/15
	Project No.	Status	Drawing No.
	N23-23	T	AR-9010
			Current Rev. No
			0