

SUPER HIGH GLOSS ENAMEL

PRODUCT CODE: 131801

(Page 1 of 3)

GENERAL DESCRIPTION

- High quality enamel for interior and exterior use.
- Superb appearance with a high gloss good build and opacity.
- Excellent durability and gloss retention.
- Wide choice of attractive colours, including national standard colours (SABS).

USES

- Recommended for the protection and decoration of interior and exterior surfaces where a glossy durable finish is required.
- Highly recommended for plaster, masonry, metal and woodwork.
- Appropriate primers and undercoats must always be used, particularly on new work.

TECHNICAL DATA

Type	-	Synthetic alkyd resin, modified long oil soya alkyd, rosin free.
Drying Time	-	Surface: 3-4 hours (at 25°C and 50% relative humidity).
	-	Hard dry: 12-16 hours (at 25°C and 50% relative humidity).
Recoating	-	16 hours.
Viscosity	-	80-85 Ku's.
Specific Gravity	-	1,08 – 1,10 (will vary according to colour).
Gloss	-	High Gloss (20° - 75% / 60° - 90% / 85° - 97%)
Weight solids	-	60 – 61% (will vary according to colour).
Volumé solids	-	44 – 45% (100µ wet film will give 45µ dry film).
Coverage (theoretical)	-	6,5 – 7m² / litre (to obtain 100% coverage with one application).
Flash Point	-	Over 21°C.
Colour range	-	White, Black and range of standard colours, as per current card.
Packing size	-	500ml, 1 litre, 5 litre, 20 litre.

All above technical data is based on Super High Gloss Enamel – White only. Coverage / spreading rate of colours depend on condition and porosity of the surface and the manner in which Dekro Super High Gloss Enamel is applied and used. As coverage will vary, a guide of standard colour coverage rates is following.

APPLICATION

- Ready for use with brush or roller.
- For spray application thin with Spraying Enamel Thinners or Mineral Turps.
- Thinning - Not recommended, except for application by spray.
- Equipment cleaning - Mineral Turps.

STANDARD APPLICATION PROCEDURE:

- New surfaces: - Remove dust, dirt and plaster splashes.
- Masonry Brick, Plaster, - Cut out large cracks and imperfections, fill with a suitable Crack Filler and sand smooth when dry.
- Asbestos, Cement - Apply one coat of Dekro ARP Plaster Primer. Ensure that surface is completely dry before application.
- Follow with one coat of Dekro Universal Undercoat prior to the application of Super High Gloss Enamel.
- Wood, Wooden surfaces - Clean to remove dust, dirt, grease etc.
- Wood composition boards - Sandpaper smooth and dust off.
- Apply knotting to all knots and sand smooth when dry.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za

e-mail: Info@dekro.co.za

SUPER HIGH GLOSS ENAMEL

PRODUCT CODE: 131801

(Page 2 of 3)

Standard Application Procedure Continued...

- | | |
|--------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Metal Surfaces
Iron and Cast Iron | <ul style="list-style-type: none"> - Spot prime all nails and metal parts with Hydrobond 44 or Dekro Alkyd Zinc Phosphate Primer. - Apply one coat of Dekro Wood Primer (white or pink). - Apply one coat Universal Undercoat prior to the application of Super High Gloss Enamel. - Clean to remove dirt, grease and oil. - Sand or grit blast to remove all rust and millscale. - If sandblasting is not viable, chip, scrape or wire brush to remove rust and loose millscale. - Where it is not possible to remove by manual methods, use chemical rust remover according to the manufacturers' instructions. - Apply one coat of Dekro Zinc Phosphate Primer or Hydrobond 44 depending on quality of final finish required. - Apply one coat of Dekro Universal Undercoat prior to the application of Super High Gloss Enamel. |
| Galvanised Iron | <ul style="list-style-type: none"> - Clean to remove dirt, grease and oil. - Use Dekro Galv-o-Clean fluid. Wash off with water and allow to dry. - Apply one coat of Dekro Vasbyt Single Pack Etch Primer or Hydrobond 44 depending on quality of final finish required. - Apply one or two coats Super High Gloss Enamel. <p>Note : This product is not suitable as a Galvanised Iron Roof paint. Use for this application Dekro Allroof Paint as directed.</p> |
| Aluminium, PVC Gutters and downpipes | <ul style="list-style-type: none"> - Pre-clean with Galv-O-Clean fluid and allow to dry. - Apply one coat of Twin Pack Etch Primer and allow to dry. - Apply one or two coats Super High Gloss Enamel. |
| Previously painted Surfaces & re-decoration Maintenance: Lime-wash | <ul style="list-style-type: none"> - Remove to bare surface by wire brushing or hydro blasting. - Remove dust and apply one coat of Dekro ARP Plaster Primer. - Apply one coat of Dekro Universal Undercoat. - Apply one or two coats Super High Gloss Enamel. |
| PVA Acrylic Emulsion, Gloss, Eggshell paint In poor condition | <ul style="list-style-type: none"> - Remove completely by scraping, wire brushing, hydro blasting, burning or paint remover to bare sound surface. - Stop and fill all large cracks and imperfections with a suitable Crack filler; allow to dry and sand smooth when dry. - Remove dust and apply one coat of ARP Plaster Primer - Apply one coat of Dekro Universal Undercoat - Apply one or two coats of Super High Gloss Enamel. |
| PVA Acrylic Emulsion Eggshell paint in good Condition | <ul style="list-style-type: none"> - Wash down with water or detergent to remove all dirt, grease and other Gloss, contaminants. - Cut out large cracks and imperfections and fill with a suitable crack filler and sand smooth when dry. - Build up bare patches with Dekro Universal Undercoat to the same level as the rest of the paintwork. Allow to dry before finishing with Super High Gloss Enamel. - For the best results, sand gloss and eggshell paint surfaces to a matt finish, rinse with water and allow to dry. - For a change in colour, apply two coats of Super High Gloss Enamel. - For general maintenance, apply one coat of Super High Gloss Enamel, depending on condition of surface and quality of finish required. |

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za

e-mail: Info@dekro.co.za

APPLICATIONS FOR AFRICA

Dekro brings paint to life...



SUPER HIGH GLOSS ENAMEL

PRODUCT CODE: 131801

(Page 3 of 3)

GENERAL

- Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
- It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PRECAUTIONS

- Do not apply direct to new galvanised iron, sand blasted steel or aluminium.
- Do not apply directly to untreated knots.
- Surfaces should not be painted in wet or damp weather.
- Unsuitable as galvanised roof paint.
- For diluting use Mineral Turps only, if required.
- Do not use Lacquer Thinners or Meths for diluting as this will alter or destroy the quality and performance of Super High Gloss Enamel.
- Clean all equipment and tools with Mineral Turps after use.
- Dry Super High Gloss Enamel can only be removed or cleaned with wax-free Paint Remover.

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za

e-mail: info@dekro.co.za