

RUBBER LINING SPECIFICATION

Parameter	Unit	Value
Polymer base	N/A	Butyl
State	N/A	Pre-cured
Thickness	mm	5
Specific weight	g/cm ³	1.17
Hardness	Shore A	60 ± 5
Tensile strength	N/mm ² or MPa	> 5
Elongation at break	%	>300
Peel strength	N/mm ²	>7
	N/mm	>2
Max. operating temperature	°C	100