



Standard

Technology

Title: **STANDARD FOR HV YARD  
STONES IN ESKOM  
TRANSMISSION SUBSTATIONS**

Unique Identifier: **240-108982466**

Alternative Reference Number: **N/A**

Area of Applicability: **Engineering**

Documentation Type: **Standard**

Revision: **1**

Total Pages: **6**

Next Review Date: **February 2022**

Disclosure Classification: **Controlled  
Disclosure**

Compiled by

Zinhle Mkhize

Design Engineer

Date: 03 - 02 - 2017

Approved by

Dawie Senekal

Senior Design Engineer

Date: 03-02-2017

Authorized by

Phineas Tlhatlhethi

Senior Manager Substation

Date: 14/02/2017

Supported by SCOT/SC

Phineas Tlhatlhethi

SCOT/SC Chairperson

Date: 14/02/2017

PCM Reference: **240-109882466**

SCOT Study Committee Number/Name: **Standard and Design Procedures – Civil (Tx)**

## 1. Introduction

This document prescribes the minimum requirements for substation HV yard stone to be used in Eskom substations. Every substation HV yard terrace should have a high resistive covering to increase the resistance of the current path through the body for personnel safety, reduce weed growth and help the ground to retain moisture.

## 2. Supporting Clauses

### 2.1 Scope

This specification covers the requirements for the stone surfacing of the yard.

#### 2.1.1 Purpose

The purpose of this document is to provide a detail specification of the yard stone to be used within Eskom Substations.

#### 2.1.2 Applicability

This document shall apply throughout Eskom Holdings Limited Divisions.

## 2.2 Normative/Informative References

### 2.2.1 Normative

- [1] ISO 9001 Quality Management Systems.
- [2] SANS 1083:2014, Aggregates from natural sources
- [3] SANS 3002:2012, Aggregates crushing value of coarse aggregates
- [4] TJ Marais, Investigation into the electrical properties of crusher stone used in substation earthing systems (Cigre IEC International Symposium – South Africa 2015)

### 2.2.2 Informative

- [5] DST 34-1245, Distribution Standard – Part 2: Earthing Section 3: Substation Earthing
- [6] TST41-877, Transmission Design Earthing Standard

## 2.3 Definitions

### 2.3.1 General

Definition	Description
<b>Crusher run (road construction material)</b>	Ungraded mixture of rock fragments and sand
<b>Mod AASHTO</b>	Modification of the laboratory test of finding the optimum moisture content (OMC) and maximum density under a standard compaction energy input as stipulated by the American Association of State Highway and Transportation Officials.
<b>Operating Unit</b>	In this document the term refers to either a Distribution Operating Unit or a Transmission Grid

**ESKOM COPYRIGHT PROTECTED**

When downloaded from the WEB, this document is uncontrolled and the responsibility rests with the user to ensure it is in line with the authorized version on the WEB.

### 3. Requirements

#### 3.1 Stone

Crushed stone shall be clean, hard, durable and sound crushed (granite) stone of aggregate size between 26,5mm and 37,5mm nominal size as stipulated in [2] and should have a wet resistivity value of at least 3000Ωm. Prior to acceptance of any crushed stone the aggregate report shall be submitted to the Substation Design Engineer for approval. The aggregate report shall include the grading result from the sieve analysis, wet resistivity values (refer to [4]) and an XRD analysis of the stone.

The above together with samples of the stone shall be submitted in good time to the design engineer for approval and no stone, other than the samples, shall be delivered to the site before the Site Supervisor's written approval has been obtained after consultation with the design engineer.

No crusher-run (road construction material or stone from mining activities (contaminated with chemicals)) will be accepted as yard stone.

#### 3.2 Construction

##### 3.2.1 Surface Preparation

After the completion of the earthworks and just before the application of the stone surfacing the Contractor shall clear the area of all vegetation growth and ensure that the underlying wearing course layer is levelled to match required terrace levels and slopes, than re-compact to 93% Mod AASHTO density.

##### 3.2.2 Laying of Stone

The stone shall be spread over the compacted surface of the yard, levelled and lightly rolled to a finished thickness of at least 100 mm or as otherwise specified in the design drawings and/or document.

##### 3.2.3 Tolerances

The average finished thickness of the stone layer shall be at least 100 mm or as otherwise specified in the design and nowhere shall the finished thickness be less than 10 mm less than the specified finished thickness.

##### 3.2.4 Contractor's Equipment

The Contractor shall ensure the provision of suitable construction equipment for the spreading of the stone in compliance with the requirements of the specification.

#### 3.3 Measurement and Payment

The rates as scheduled in the Bill of Quantities shall cover the cost of all activities, labour, materials and testing required for the provision of the relative item in accordance with the design/drawings and specifications.

### 4. Authorisation

This document has been seen and accepted by:

Name and surname	Designation
Phineas Tlhatlhetji	Senior Manager – Substation Engineering
Theunus Marais	Chief Engineer – Substation Engineering
Dawie Senekal	Senior Engineer – Substation Engineering
Krishna Naidoo	Senior Engineer – Substation Engineering

ESKOM COPYRIGHT PROTECTED

When downloaded from the WEB, this document is uncontrolled and the responsibility rests with the user to ensure it is in line with the authorized version on the WEB.

Name and surname	Designation
Mohammad Nabbie	Senior Engineer – Substation Engineering
Thato Seatlholo	Senior Technician – Substation Engineering
Zinhle Mkhize	Design Engineer – Substation Engineering

## 5. Revisions

Date	Rev	Compiler	Remarks
Feb 2017	1	Z.I Mkhize	New document required

## 6. Development team

The following people were involved in the development of this document:

- Zinhle Mkhize
- Dawie Senekal
- Thato Seatlholo

## 7. Acknowledgements

Krishna Naidoo, Mohammad Nabbie and Theunus Marais for inputs